

## TYPE:

QUICK AIR DRYING ALKYD RESIN BASED ON SOYABEAN FATTY ACID

## DELIVERY FORM:

JSB-PU309-X 65 65±1 % in Toluene

## INTRODUCTION:

<u>SPECIFICATIONS</u>	<i>PU309-X65</i>
Oil type	Soya Fatty Acid
Oil Content	38 ± 1 %
Acid value (max)	10
Viscosity @ 25 °c (stoke)	55-70
Density	1.03 ± 0.02
Color (Gardner)	6 MAX
Non-volatile content	65 ± 1
Solvent (s)	Toluene

## PROPERTIES:

- Very good yellowing resistance
- excellent elasticity
- Compatible with acrylic resins.
- Good water resistance

## APPLICATIONS:

- Quick air drying
- Top coats
- Hammer paints

## SOLUBILITY:

Methyl Isobutyl Ketons, Xylene , white spirit (limited), Butyl Acetate , other alkyd resins, Amino resin

## STORAGE & STABILITY:

The shelf life of the products is 24 months if kept in a cool and dry place (5-30°C) in original sealed drums. Keep away from any source of heat

پیشنهادات ذکر شده در این کاتالوگ بر اساس تحقیقات و آزمایشات ما می باشد لذا خواهشمندیم قبل از استفاده کیفیت و تمامی خواص رزین بررسی شود.