

TYPE:

SHORT OIL ALKYD RESIN BASED ON SOYA FATTY ACIDS

DELIVERY FORM:

JSB-EUA-X- 60 60±1 % in xylene

INTRODUCTION:

Short oil Alkyd Resins are based on soya fatty acids and Pentaerythritol or Glycerol, and are classified accordingly in two groups of air-drying and non-drying.

<u>SPECIFICATIONS</u>	<i>EUA-X-60</i>
Oil type	Soya Fatty Acid
Oil Content	23%
Acid value (max)	11-13
Viscosity @ 25 °c (stoke)	30-40
Color (Gardner)	3-5
Non-volatile content	60 ±1
Solvent (s)	Xylene

PROPERTIES:

- Quick dry
- High gloss
- Good hardness & abrasion

APPLICATIONS:

- Hammer finishes
- NC lacquer undercoat & enamels
- Fast dry industrial enamels
- Force drying enamels

SOLUBILITY:

Alcohols (Limited), esters, ketons, acetates, aromatics, glycols. Acetate ,

STORAGE & STABILITY:

The shelf life of the products is 24 months if kept in a cool and dry place (5-30°C) in original sealed drums. Keep away from any source of heat.

THE OFFERED RECOMMENDATIONS ARE BASED UPON OUR EXISTING KNOWLEDGE MERELY TO BE DEEMED AS START FORMULATIONS. THEREFORE, THERE IS NO GUARANTEE, I.E., WE ASSUME NO LIABILITY IN THIS REGARD AND THIS IS BECAUSE THE APPLICATION METHODS AND CONSUMPTION CONDITIONS ARE OUT OF OUR CONTROL. HENCE, THE ESTEEMED CONSUMERS ARE TO EVALUATE THE FORMULATIONS IN THEIR OWN LABS PRIOR TO PRODUCTION.