

TYPE:

ZIRCONIUM DRIER

DELIVERY FORM:

JSB-ZR-18

PROPERTIES:

- Reduced and speed up curing time.
- Good pigment wetting
- Excellent drying power
- Resistance to Settling

<u>SPECIFICATIONS</u>	<i>ZIRCONIUM DRIER</i>
Apearance	Yellow liquid
Metal Content	18 ± 2
Density (25C° and g / cc)	1.27± 0.02
Solvent (s)	Xylene

SOLUBILITY:

Methyl Ethyl Ketons, Xylene , N-Butyl Acetate, N- Butanol (limited) , Mineral spirit (limited)

STORAGE & STABILITY:

The shelf life of the products is 12 months if kept in a cool and dry place (5-30 °C) in original sealed drums. Keep away from any source of heat.

PACKING:

250 kg net in new iron drum.

COMPATIBILITY:

Compatibility with long and medium Alkyd resins and the other driers such as Cobalt, Manganese and Calcium. it must be checked before use.

THE OFFERED RECOMMENDATIONS ARE BASED UPON OUR EXISTING KNOWLEDGE MERELY TO BE DEEMED AS START FORMULATIONS. THEREFORE, THERE IS NO GUARANTEE, I.E., WE ASSUME NO LIABILITY IN THIS REGARD AND THIS IS BECAUSE THE APPLICATION METHODS AND CONSUMPTION CONDITIONS ARE OUT OF OUR CONTROL. HENCE, THE ESTEEMED CONSUMERS ARE TO EVALUATE THE FORMULATIONS IN THEIR OWN LABS PRIOR TO PRODUCTION.