

JSB-DR-15

TYPE:

SPECIAL DRIER FOR HAMMER PAINT

DELIVERY FORM:

JSB-DR-15

PROPERTIES:

- Reduced and speed up curing time.
- Good pigment wetting

APPLICATIONS:

addition rate of consumption is 1.3% PHR (part per hundred of resin, by weight)

SPECIFICATIONS: DR-15

Apearence: : violent liquid

Solvent : xylene

SOLUBILITY:

Normal Butanol (limited), Methyl Ethyl Ketons, white spirite (limited), Xylene

STORAGE & STABILITY:

The shelf life of the products is 12 months if kept in a cool and dry place (5-30 °C) in original sealed drums. Keep away from any source of heat.

PACKING:

200 kg net in new iron drum.

COMPATIBILITY:

Compatibility Short Alkyd resins and the other driers such as lead, Cobalt and Calcium. it must be checked before use.

THE OFFERED RECOMMENDATIONS ARE BASED UPON OUR EXISTING KNOWLEDGE MERELY TO BE DEEMED AS START FORMULATIONS. THEREFORE, THERE IS NO GUARANTEE, I.E., WE ASSUME NO LIABILITY IN THIS REGARD AND THIS IS BECAUSE THE APPLICATION METHODS AND CONSUMPTION CONDITIONS ARE OUT OF OUR CONTROL. HENCE, THE ESTEEMED CONSUMERS ARE TO EVALUATE THE FORMULATIONS IN THEIR OWN LABS PRIOR TO PRODUCTION.

Office: Unit 4, No.4, North Motahary St., Darya Blvd., Saadat Abad, Tehran, Iran Tel: 0098 21 88698817, 0098 21 88696553, Fax: 0098 21 88699083 Factory: 255 St., South Ebtekar St., Ebtekar Square, Shaharak sanati bozorg, Shiraz, Iran

Tel: 0098 711 7742121-2 ,Fax: 0098 711 7743995

دفتر: تهران، سعادت آباد، بلوار دریا، خیابان مطهری شمالی، پلاک ٤ واحد ٤ تلفن: ۱۸۸۶۹۶۸۸۱۷ فکس: ۸۸۶۹۹۸۸۱۷ فکس: ۲۱ ۸۸۶۹۸۸۱۷ فکس تلفن: ۲۵۸ ۲۵۸ تلفن: ۲-۷۱۱ ۷۷٤۲۱۲۱ فکس: ۷۱۱ ۷۷٤۲۱۲۱۰ فکس: ۷۱۱ ۷۷۲۲۲۱۲۱۰